

## Technical Data Sheet

### D.P.S. STRETCHFILM – Cod. DPS2-10M

Preliminary, provisional design. D.P.S. Stretch Film is undergoing continuous development, which means that the values below are subject to change.

A warranty for the suitability can not be derived from these values.

The production takes place on the basis of the ProStretch - supplier declaration.

#### Item description: D.P.S. STRETCHFILM DPS2-10M

Stretch film type NG2 with double edge for manual processing, prestretched transparent, without print, 1 side cling, 1 side smooth

Film attribute	Unit	Value	Testing metod
Film thickness	µm	10	DIN 53370
Film width	mm	450	DIN 53370
Roll length	m	600	DIN 53370
Core diameter inside	mm	50	DIN 53370
Weight	Kg	2,49 + core	/
Pallet	rolls /pallet	216	
Coefficient of friction (COF)	/	0.3 – 0.4	DIN EN ISO 8295 film /metal
Tear growth resistance crossways (TD)	N	> 4.5	Elmendorf DIN 53128

Life cycle of the film:

1. It is recommended to use our product within 12 months from the date of manufacture.
2. The product should be stored between 15-30 °C and 40-70 % RH and not be exposed to direct sunshine or heat.

Handling and storage:

3. Handle the pallets with care. It is not allowed to store the pallets on top of each other. The rolls should be stored in a good vented and cool place, far away from incompatible other materials.
4. Do not handle, store or open nearby open fire, heat or ignition sources. Protect the material from direct solar radiation. The material can be charged electrostatically, whereby sparks can emerge (ignition source).

The specified attribute standard values are based on our current knowledge and experiences.

They do not constitute warranty of particular attributes.

We reserve the right to develop our products continuously.

The user has to conduct own tests with our products prior to application. This is particularly vital concerning the suitability for a particular application.

The same is valid correspondingly for general terms and conditions apply.

Plastofilm srl

Via Fondovilla 84/c – 36010 Carrè (VI) Italy – tel. +39 0445 1922112 – mail: [info@plastofilm.it](mailto:info@plastofilm.it)

[www.plastofilm.it](http://www.plastofilm.it) - [www.shop.plastofilm.it](http://www.shop.plastofilm.it)